

COLOUR CHART

Fugalite® Bio Parquet colours		Colour Fastness* GSc (Daylight) EN ISO 105-A05 standard
54 Larix		4
55 Betula		3,5
56 Acer		3,5
57 Fraxinus		4
58 Fagus		4,5
59 Ulmus		4,5
60 Quercus		4,5
61 Castanea		4,5
62 Milicia		4,5
63 Afzelia		4,5
64 Tectona		4,5
65 Millettia		4,5
Legend	from 5 to 4 high colour fastness; for internal and external use from 3.5 to 3 good colour fastness; for internal and external use from 2.5 to 1 limited colour fastness; for internal use	<i>The shades shown are intended as an indication only, for colour selection please refer to the Fugalite® Bio Parquet colour chart.</i>

* Samples were exposed for 500 hours to a light spectrum equivalent to natural sunlight at midday, at the height of the summer on the earth's surface in the northern hemisphere. Differences in clarity, saturation and hue as compared to the reference sample kept in the dark in standard conditions are measured.

The resulting colour difference ΔE_f is used to calculate the grey scale intensity values for colour fastness (GSC), expressed in a range from 5 (maximum fastness) to 1.

Important: the human eye cannot distinguish colour differences in the 5 to 3 range.